



Test items	Test method	Test value
Gaugethickness (mm)	Teclock SM-114	0,3
(A) Hardness	ASTM-2240 SHORE A	88
(kgf) Tensile	ASTM-D412 (C)	
(kgf) Tensile	ASTM-D412 (C)	17,47
(Mpa) Tensile strength	ASTM-D412 (C)	45,3
(Mpa) Tensile strength	ASTM-D412 (C)	40,8
(%) Elongation	ASTM-D412 (C)	627,5
(%) Elongation	ASTM-D412 (C)	712,4
(kgf/cm) Tear strength	ASTM-D624	136,1
(kgf/cm) Tear strength	ASTM-D624	114,0
(°C) Point		153
(g/cm <sup>3</sup> ) Gravity		1,11
remarks	8 GX-8002 (JD-306S) °C, %RH	